

Edgetherm PIB-H1 insulating glass sealant is a high viscosity, high strength, 100% solids sealant based on polyisobutylene polymer formulated to impart reinforcement, resist degradation from ultraviolet light, and provide low moisture permeability.

Basic Use

Used as the primary seal on insulating glass units while providing the main moisture vapor seal between the glass and spacer. Edgetherm PIB H-1 must be used with a secondary seal designed to provide structural strength.

Colors

Edgetherm PIB-H1 is available in black.

Packaging & Sizes

Edgetherm PIB-H1 is available in bulk (slug form) for application by various type extruders.

- Slugs: 7.5" D x 9.5" H (15 lb/7kg)

Shelf Life

Two years from date of manufacture.

Technical Services

Your Quanex Building Products Representative, in conjunction with your Quanex Building Products Technical Service Group, can provide in-plant training and assistance with special applications.

Availability/Cost

Availability and cost can be obtained from your local Quanex Representative or by calling our Customer Service Center. For more information call Truseal, a Quanex Building Products company: in the U.S. 888-910-5280; in Canada 888-794-4453.

Storage Conditions

Store in original package, indoors, away from rain and out of standing water.

Performance	Norm
Moisture Vapor Transmission Rate 0.45 g/m ² /d, 0.060" film, 100° F, 100% RH	ASTM F 1249
Volatile Fogging Passes	ASTM 2189
Shear Resistance @ 2 psi Time to displace 0.2" 28 minutes Time to displace 1.0" 75 minutes	
Weight per Gallon (Specific Gravity) Black: 9.34 lb/U.S. gal (1.12 g/cc)	
Hardness (Consistency) 40 dmm	ASTM D 5
Note: The foregoing information is published as general information only. The listed properties and performance characteristics are approximate value and are not part of the product specification.	

Glazing Compatibility and Design Recommendations

In general, materials such as hot-applied sealants, silicones, glazing tapes and solvent acrylics are compatible. However, it is recommended that glazing materials be tested for compatibility. Fabricated units shall be glazed in accordance with GANA (Glass Association of North America) and IGMA (Insulating Glass Manufacturers Alliance) recommendations. Please check with your Quanex Representative for specific glazing recommendations.

Health & Safety

For all Quanex products, and for other product used in conjunction with Quanex products, users must follow individual product labels and Material Safety Data Sheets for warnings and precautions prior to opening containers and during use and storage.

Warranty

See Truseal warranty certificate.

EdgeTherm® is a registered trademark of Truseal Technologies, Inc.

Quanex recommends you visit www.Quanex.com and register to ensure you have the most current updates to this data and all other Quanex sales and technical materials.

Key Features Summary

- Easy application and handling of coated spacer bars
- High viscosity formula resists shearing in large, heavy lites of glass
- Edgetherm PIB-H1 has excellent adhesion to glass and metal through a wide temperature range
- Non-fogging (100% solids)
- Consistent quality
- Retains flexibility through a wide temperature range to compensate for thermal movement of the insulating glass unit
- Edgetherm PIB-H1 resists degradation from ultraviolet light and oxidation
- Edgetherm PIB-H1 features a low moisture vapor transmission rate



Quanex warm-edge IG spacer systems are used by our customers to assemble ENERGY STAR® qualified windows and doors.



ISO 9001:2008,
Certificate Registration 10001512 QM08